Synthesis and characterization of (Bi,Cu)Sr₂(RE,Ca)Cu₂O_z

著者	Maeda Toshihiko, Tashiro Tairiku, Horii Shigeru
journal or publication title	Physica C: Superconductivity
volume	470
page range	S31-S32
year	2010-12
URL	http://hdl.handle.net/10173/638

doi: 10.1016/j.physc.2010.01.013

Elsevier Editorial System(tm) for Physica C

Manuscript Draft

Manuscript Number: PHYSC-D-09-00727

Title: Synthesis and characterization of $(\text{Bi,Cu})\text{Sr}_2(\text{RE,Ca})\text{Cu}_2\text{O}_z$ (RE: Y or rare-earth element)

Article Type: Special Issue: M²S IX

Keywords: $(\text{Bi,Cu})\text{Sr}_2(\text{RE,Ca})\text{Cu}_2\text{O}_z$; chemical composition; rare-earth substitution; Ca solubility

Corresponding Author: Prof. Toshihiko Maeda,

Corresponding Author's Institution: Department of environmental systems engineering, Kochi University of Technology, Miyanokuchi 185, Tosayamada-cho, Kami-shi, Kohi 782-8502, Japan.

First Author: Toshihiko Maeda, Prof.

Order of Authors: Toshihiko Maeda, Prof.; Tairiku Tashiro, Mr.; Shigeru Horii, Prof.

Abstract: Samples with nominal compositions of $x=0\sim 0.1$ in $(\text{Bi}_{(1+3x)/3}\text{Cu}_{(2-3x)/3})\text{Sr}_2(\text{RE}_{1-x}\text{Ca}_x)\text{Cu}_2\text{O}_z$ ((Bi,Cu)-"1-2-1-2"; RE: Y or rare-earth element) were synthesized by a solid-state reaction method and characterized by means of X-ray diffractometry (XRD). It is confirmed that the (Bi,Cu)-"1-2-1-2" forms only when RE=Y, Dy and Ho. Single- or nearly single-phase samples are obtained for $x=0\sim 0.05$ and the Ca-free composition of this compound is determined to be $(\text{Bi}_{1/3}\text{Cu}_{2/3})\text{Sr}_2\text{RECu}_2\text{O}_z$. Since ionic radii of Y, Dy and Ho are very close to each other and this seems to be an essential factor for the stability of the (Bi,Cu)-"1-2-1-2".

1. Introduction

Observation of superconductivity at critical temperature (T_c) of 68 K in a Ca-free sample with a nominal composition of $(\text{Bi}_{0.5}\text{Cu}_{0.5})\text{Sr}_2\text{Y}_{0.8}\text{Cu}_{2.2}\text{O}_z$ has been reported for the first time by Ehmann *et al.* [1]. They suggested that the real chemical composition of this compound was $(\text{Bi,Cu})\text{Sr}_2(\text{Y,Ca})\text{Cu}_2\text{O}_z$ and that its idealized crystallographic structure was so-called "1-2-1-2" type characteristically containing $(\text{Bi,Cu})\text{O}$ monolayer. It was likely that this compound had a tetragonal unit cell with a space group of P4/mmm having lattice parameters of $a \approx 0.38$ nm and $c \approx 1.17$ nm [1,2]. Real chemical composition of this $(\text{Bi,Cu})\text{Sr}_2(\text{Y,Ca})\text{Cu}_2\text{O}_z$ ((Bi,Cu)-"1-2-1-2"), however, seems to have not yet been made clear especially on the viewpoint of Bi/Cu ratio in the $(\text{Bi,Cu})\text{O}$ monolayer and Ca substitution for the Y site. In this study, preparation of single-phase samples with Ca-doping and replacement of the Y sites by some rare-earth species were attempted for the (Bi,Cu)-"1-2-1-2".

2. Experimental

Samples were synthesized by solid-state reaction of commercial reagents of Bi_2O_3 , SrCO_3 , RE_2O_3 (RE: Y, La, Nd, Sm, Eu, Gd, Dy, Ho and Er), CaCO_3 and CuO with 3N-up purity. These powders were mixed according to the nominal metallic composition of $(\text{Bi}_{1/3+x}\text{Cu}_{2/3-x})\text{Sr}_2(\text{RE}_{1-x}\text{Ca}_x)\text{Cu}_2\text{O}_z$ ($x=0\sim 0.1$) using an agate mortar. The obtained powder mixtures were calcined at 850°C for 10 h in air gas mixture. The calcined powders were again pulverized and pelletized, and then finally sintered at $940\sim 1090^\circ\text{C}$ (according to RE species) for 10 h in air. The obtained black-colored ceramics samples were structurally analyzed by means of X-ray diffractometry (XRD) using $\text{CuK}\alpha$ radiation.

3. Results and discussion

3-1. (Bi,Cu)Sr₂(Y,Ca)Cu₂O_z

For the case of RE=Y, preliminary XRD results showed that chemical composition of the Ca-free end member of the (Bi,Cu)"1-2-1-2" seemed to be very close to (Bi_{0.7}Cu_{0.3})Sr₂YCu₂O_z and that partial substitution of Ca for Y site did not result in single-phase samples when Bi/Cu ratio in the (Bi,Cu) site was fixed at 0.7/0.3. Therefore, we selected the above mentioned (Bi_{1/3+x}Cu_{2/3-x})Sr₂(RE_{1-x}Ca_x)Cu₂O_z as starting compositions according to the case of (Pb_{(1+x)/2}Cu_{(1-x)/2})Sr₂(Y_{1-x}Ca_x)Cu₂O_z [3] which was isomorphous to the (Bi,Cu)"1-2-1-2". If valence state of Bi ion was +3, this composition meant that the decrease of positive charge of (Y³⁺,Ca²⁺) site induced by the Ca substitution was completely compensated by the change in Bi/Cu ratio in the (Bi³⁺,Cu²⁺) site.

Figure 1 shows XRD profiles for samples of RE=Y with nominal compositions of $x=0, 0.025, 0.05$ and 0.075 sintered at 965°C . Most of the diffraction lines for each sample could be indexed according to the typical "1-2-1-2" structure. For the case of RE=Y, it should be noted that single-phase samples of (Bi,Cu)"1-2-1-2" were obtained only in a quite narrow temperature range of $965\sim 970^{\circ}\text{C}$ when sintered in air for 10 h. As shown in Fig. 1, single- or nearly single-phase samples were obtained for $x=0\sim 0.05$ while several additional diffraction lines derived from secondary phase(s) clearly appeared in the diffraction patterns for $x=0.075$ and 0.1 .

From these results, it can be concluded that the chemical composition of the Ca-free end member should be just (Bi_{1/3}Cu_{2/3})Sr₂YCu₂O_z or at least quite close to it and that Ca solubility for the Y site seems not to exceed 0.05. The values of lattice constants, a and c , were estimated using 2θ values of respectively (200) and (006) diffraction lines. For

all of x , a and c were ranged in 0.3814~0.3818 and 1.171~1.172 nm, respectively, and no systematic change with x were seen probably because of the limitation of experimental accuracy due to too small amount of doped Ca.

In the (Bi,Cu)-"1-2-1-2", the valence state of Bi ion is thought to be in 3+ similarly as in other Bi-containing superconducting cuprates, for example, $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$ and $\text{Bi}_2\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_{10}$. This seems to suggest that fairly large amount of oxygen deficiency exists in the present (Bi/Cu)-"1-2-1-2". If Bi and Cu ions in the (Bi/Cu)-"1-2-1-2" are respectively in 3+ and in 2+, oxygen content z in $(\text{Bi}_{1/3}\text{Cu}_{2/3})\text{Sr}_2\text{YCu}_2\text{O}_z$ ($x=0$) should be ideally 6.67 since Sr and Y ions are in 2+ and in 3+, respectively. This is probably essential for the occurrence of superconductivity in this compound and investigation on this point is now in progress.

3-2. $(\text{Bi,Cu})\text{Sr}_2(\text{RE,Ca})\text{Cu}_2\text{O}_z$ (RE=Dy and Ho)

Attempt was made to synthesize (Bi,Cu)-"1-2-1-2" using several rare-earth species (La, Nd, Sm, Eu, Gd, Dy, Ho and Er) instead of Y, and it was confirmed that (Bi,Cu)-"1-2-1-2" did not form for most of RE species except for Dy and Ho. It should be noted that, in the XRD results, any trace of formation of (Bi,Cu)-"1-2-1-2" was not observed for RE's other than Dy and Ho. Figures 2 and 3 show XRD profiles for samples of RE=Dy and RE=Ho respectively. The ionic radii of Y^{3+} , Dy^{3+} and Ho^{3+} with coordination number of 8 are 1.019, 1.027 and 1.015 nm, respectively [4] and these values are very close to each other. Therefore, it is likely that the ionic radius of RE species is one of the most crucial factors to stabilize (Bi,Cu)-"1-2-1-2" structure. The origin of this phenomenon is not so clear but this is interesting on the viewpoint of crystal chemistry. Single- or nearly single-phase (Bi,Cu)-"1-2-1-2" were obtained for $x=0\sim0.1$ as seen in the figures while significant change in lattice parameters with x was

not observed similarly as the case of RE=Y.

4. Conclusion

Chemical composition and phase formation of (Bi,Cu)-"1-2-1-2" were investigated. Using nominal composition of $(\text{Bi}_{1/3+x}\text{Cu}_{2/3-x})\text{Sr}_2(\text{Y}_{1-x}\text{Ca}_x)\text{Cu}_2\text{O}_z$, nearly single-phase samples were obtained for x up to 0.05. The (Bi,Cu)-"1-2-1-2" was proved to form in very narrow temperature window of 965~970°C. Using several RE species instead of Y, the (Bi,Cu)-"1-2-1-2" was obtained only for Dy and Ho. Ionic radius of the RE^{3+} ions is likely to be one of the most crucial factors for the stability of this phase.

References

- [1] A. Ehmman, S. Kemmler-Sack, S. Lösch, M. Schlichenmaier, W. Wischert, P. Zoller, T. Nissel, R. P. Huebener, *Physica C* 198 (1992) 1.
- [2] H. -U. Nissen, M. Cantoni, S. Kemmler-Sack, A. Ehmman, S. Lösch, W. Wischert, P. Zoller, *Physica C* 203 (1992) 436.
- [3] T. Maeda, K. Sakuyama, S. Koriyama, H. Yamauchi, S. Tanaka, *Phys. Rev. B* 43 (1991) 7866.
- [4] R. D. Shannon, *Acta Crystallogr. A* 32, 751 (1976).

Figure captions

Fig. 1. XRD profiles for samples of RE=Y.

Fig. 2. XRD profiles for samples of RE=Dy.

Fig. 3. XRD profiles for samples of RE=Ho.

Intensity/a.u.

Intensity/a.u.

Intensity/a.u.